

# RIVERBANK ACOUSTICAL LABORATORIES

1512 S. BATAVIA AVENUE  
GENEVA, ILLINOIS 60134

Alion Science and Technology

630/232-0104  
FOUNDED 1918 BY  
WALLACE CLEMENT SABINE

## TEST REPORT

FOR: Asona-USA, LLC  
Sandusky, OH.

Sound Absorption  
RAL™-A14-063

CONDUCTED: 18 March 2014

Page 1 of 6

ON: 1 inch thick, 6pcf fiberglass panels with Sonacoustic SM (Smooth Plaster Finish)

### TEST METHOD

The test method conformed explicitly with the requirements of the ASTM Standard Test Method for Sound Absorption and Sound Absorption Coefficients by the Reverberation Room Method: ASTM C423-09a and E795-05. Riverbank Acoustical Laboratories has been accredited by the U.S. Department of Commerce, National Institute of Standards and Technology (NIST) under the National Voluntary Laboratory Accreditation Program (NVLAP) for this test procedure (NVLAP Lab Code: 100227-0). A description of the measuring procedure and room qualifications is available separately.

### DESCRIPTION OF THE SPECIMEN

The test specimen was designated by the manufacturer as: 1 inch thick, 6pcf fiberglass panels with Sonacoustic SM (Smooth Plaster Finish). A visual inspection by Riverbank staff verified the manufacturer's description. The specimen consisted of 6 pieces of rigid fiberglass board (6 pcf.) each measured as 1.24 m (49.0 in) long by 914.4 mm (36.0 in) wide and 25.4 mm (1.0 in) thick. A layer of Sonacoustic base and finish plaster, measured as 2.0 mm (0.08 in) thick, were applied to the face of the specimen. The finish plaster was applied over the base plaster with a trowel and polished.

Laid together as a single rectangular patch, the overall dimensions of the specimen as measured were 2.49 m (98.00 in.) wide by 2.74 m (108.00 in.) long and 27.40 mm (1.08 in.) thick. The area used in the calculations was 6.83 m<sup>2</sup> (73.50 ft<sup>2</sup>). The weight of the entire specimen as measured was 21.43 kg (47.25 lbs), an average of 3.12 kg/m<sup>2</sup> (0.64 lbs/ft<sup>2</sup>).

The specimen was tested in the laboratory's 292.0 m<sup>3</sup> (10,311.0 ft<sup>3</sup>) test chamber. The room temperature at the time of the test was 20.9±0.0°C (69.7±0.0°F) and 62.2±0.9% relative humidity. The atmospheric pressure was 98.3 kPa.



NVLAP LAB CODE 100227-0

RAL IS ACCREDITED BY THE US DEPARTMENT OF COMMERCE, NATIONAL VOLUNTARY LABORATORY ACCREDITATION PROGRAM FOR SPECIFIC ACOUSTICAL TEST METHODS. THE LABORATORY'S ACCREDITATION OR ANY OF ITS TEST REPORTS IN NO WAY CONSTITUTES OR IMPLIES PRODUCT CERTIFICATION, APPROVAL OR ENDORSEMENT BY NIST OR RAL.

THIS REPORT SHALL NOT BE MODIFIED OR PARTIALLY REPRODUCED WITHOUT THE WRITTEN APPROVAL OF RAL.

THE RESULTS REPORTED APPLY ONLY TO THE SPECIFIC SAMPLE SUBMITTED FOR MEASUREMENT; RAL ASSUMES NO RESPONSIBILITY FOR THE PERFORMANCE OF ANY OTHER SPECIMEN.

# RIVERBANK ACOUSTICAL LABORATORIES

1512 S. BATAVIA AVENUE  
GENEVA, ILLINOIS 60134

Alion Science and Technology

630/232-0104  
FOUNDED 1918 BY  
WALLACE CLEMENT SABINE

## TEST REPORT

Asona-USA, LLC  
18 March 2014

RAL™-A14-063  
Page 2 of 6




Figure 1 - Specimen mounted in the test chamber.



Figure 2 - Detail of the test specimen.



NVLAP LAB CODE 100227-0

RAL IS ACCREDITED BY THE US DEPARTMENT OF COMMERCE, NATIONAL VOLUNTARY LABORATORY ACCREDITATION PROGRAM FOR SPECIFIC ACOUSTICAL TEST METHODS. THE LABORATORY'S ACCREDITATION OR ANY OF ITS TEST REPORTS IN NO WAY CONSTITUTES OR IMPLIES PRODUCT CERTIFICATION, APPROVAL OR ENDORSEMENT BY NIST OR RAL.

THIS REPORT SHALL NOT BE MODIFIED OR PARTIALLY REPRODUCED WITHOUT THE WRITTEN APPROVAL OF RAL.

THE RESULTS REPORTED APPLY ONLY TO THE SPECIFIC SAMPLE SUBMITTED FOR MEASUREMENT; RAL ASSUMES NO RESPONSIBILITY FOR THE PERFORMANCE OF ANY OTHER SPECIMEN.

# RIVERBANK ACOUSTICAL LABORATORIES

1512 S. BATAVIA AVENUE  
GENEVA, ILLINOIS 60134

Alion Science and Technology

630/232-0104  
FOUNDED 1918 BY  
WALLACE CLEMENT SABINE

## TEST REPORT

Asona-USA, LLC  
18 March 2014

RAL™-A14-063  
Page 3 of 6

### MOUNTING A

The test specimen was laid directly against the test surface. The perimeter was sealed using metal framing.

### TEST RESULTS

1/3 Octave Center Frequency (Hz)	Absorption Coefficient (Sabins / ft <sup>2</sup> )	Total Absorption In Sabins
100	0.06	4.42
** 125	0.28	20.24
160	0.32	23.58
200	0.40	29.34
** 250	0.62	45.38
315	0.83	61.36
400	0.87	63.64
** 500	0.95	69.47
630	0.92	67.80
800	0.94	68.97
** 1000	0.99	73.06
1250	0.94	69.06
1600	0.87	63.89
** 2000	0.86	63.22
2500	0.81	59.82
3150	0.80	58.56
** 4000	0.79	58.05
5000	0.82	60.57

**SAA = 0.83**  
**NRC = 0.85**



NVLAP LAB CODE 100227-0

RAL IS ACCREDITED BY THE US DEPARTMENT OF COMMERCE, NATIONAL VOLUNTARY LABORATORY ACCREDITATION PROGRAM FOR SPECIFIC ACOUSTICAL TEST METHODS. THE LABORATORY'S ACCREDITATION OR ANY OF ITS TEST REPORTS IN NO WAY CONSTITUTES OR IMPLIES PRODUCT CERTIFICATION, APPROVAL OR ENDORSEMENT BY NIST OR RAL.

THIS REPORT SHALL NOT BE MODIFIED OR PARTIALLY REPRODUCED WITHOUT THE WRITTEN APPROVAL OF RAL.

THE RESULTS REPORTED APPLY ONLY TO THE SPECIFIC SAMPLE SUBMITTED FOR MEASUREMENT; RAL ASSUMES NO RESPONSIBILITY FOR THE PERFORMANCE OF ANY OTHER SPECIMEN.

# RIVERBANK ACOUSTICAL LABORATORIES

1512 S. BATAVIA AVENUE  
GENEVA, ILLINOIS 60134

Alion Science and Technology

630/232-0104  
FOUNDED 1918 BY  
WALLACE CLEMENT SABINE

## TEST REPORT



Asona-USA, LLC  
18 March 2014

RAL™-A14-063  
Page 4 of 6

### TEST RESULTS (Continued)

The sound absorption average (SAA) is defined as a single number rating, the average, rounded to the nearest 0.01, of the sound absorption coefficient of a material for the twelve one-third octave bands from 200 through 2500 Hz, inclusive.

The noise reduction coefficient (NRC) is defined from previous versions of this same test method as the average of the coefficients at 250, 500, 1000, and 2000 Hz, expressed to the nearest integral multiple of 0.05.

Tested by  Approved by   
Marc Sciaky  
Experimentalist  
Eric P. Wolfram  
Laboratory Manager



NVLAP LAB CODE 100227-0

RAL IS ACCREDITED BY THE US DEPARTMENT OF COMMERCE, NATIONAL VOLUNTARY LABORATORY ACCREDITATION PROGRAM FOR SPECIFIC ACOUSTICAL TEST METHODS. THE LABORATORY'S ACCREDITATION OR ANY OF ITS TEST REPORTS IN NO WAY CONSTITUTES OR IMPLIES PRODUCT CERTIFICATION, APPROVAL OR ENDORSEMENT BY NIST OR RAL.

THIS REPORT SHALL NOT BE MODIFIED OR PARTIALLY REPRODUCED WITHOUT THE WRITTEN APPROVAL OF RAL.

THE RESULTS REPORTED APPLY ONLY TO THE SPECIFIC SAMPLE SUBMITTED FOR MEASUREMENT; RAL ASSUMES NO RESPONSIBILITY FOR THE PERFORMANCE OF ANY OTHER SPECIMEN.

# RIVERBANK ACOUSTICAL LABORATORIES

1512 S. BATAVIA AVENUE  
GENEVA, ILLINOIS 60134

Alion Science and Technology

630/232-0104  
FOUNDED 1918 BY  
WALLACE CLEMENT SABINE


## TEST REPORT

Asona-USA, LLC  
18 March 2014

RAL™-A14-063  
Page 5 of 6

### SOUND ABSORPTION REPORT

1 inch thick, 6pcf fiberglass panels with Sonacoustic SM (Smooth Plaster Finish)



**SAA = 0.83**  
**NRC = 0.85**



NVLAP LAB CODE 100227-0

RAL IS ACCREDITED BY THE US DEPARTMENT OF COMMERCE, NATIONAL VOLUNTARY LABORATORY ACCREDITATION PROGRAM FOR SPECIFIC ACOUSTICAL TEST METHODS. THE LABORATORY'S ACCREDITATION OR ANY OF ITS TEST REPORTS IN NO WAY CONSTITUTES OR IMPLIES PRODUCT CERTIFICATION, APPROVAL OR ENDORSEMENT BY NIST OR RAL.

THIS REPORT SHALL NOT BE MODIFIED OR PARTIALLY REPRODUCED WITHOUT THE WRITTEN APPROVAL OF RAL.

THE RESULTS REPORTED APPLY ONLY TO THE SPECIFIC SAMPLE SUBMITTED FOR MEASUREMENT; RAL ASSUMES NO RESPONSIBILITY FOR THE PERFORMANCE OF ANY OTHER SPECIMEN.

# RIVERBANK ACOUSTICAL LABORATORIES

1512 S. BATAVIA AVENUE  
GENEVA, ILLINOIS 60134

Alion Science and Technology

630/232-0104  
FOUNDED 1918 BY  
WALLACE CLEMENT SABINE

## TEST REPORT

Asona-USA, LLC  
18 March 2014

RAL™-A14-063  
Page 6 of 6

### Appendix to ASTM C423 Sound Absorption Test **Extended Frequency Range Data**

Product Description: 1 inch thick, 6pcf fiberglass panels with Sonacoustic SM (Smooth Plaster Finish) (See Full Report)

Riverbank Acoustical Laboratories is accredited to perform sound absorption coefficient measurements for the frequency range of 100Hz to 5,000Hz. However, we calculate sound absorption values at additional test frequencies as a service to our clients.

Although these measurements were made in accordance with the procedures described in ASTM C423-09a, they do not qualify as part of the standard. Since the results are representative of the test environment only, they are unofficial and intended for research and development guidelines rather than for commercial purposes. The sound absorption values at additional frequencies were as follows:

#### **RAL-A14-063**

<b>1/3 Octave Center Frequency</b> <b>(Hz)</b>	<b>Absorption</b> <b>Coefficient</b> <b>(Sabins / ft<sup>2</sup>)</b>	<b>Total Absorption</b> <b>(Sabins)</b>
40	0.00	0.26
50	0.40	29.40
63	-0.12	-8.64
80	0.05	3.54
6300	0.75	55.14
8000	0.59	43.67
10000	0.59	43.09



NVLAP LAB CODE 100227-0

RAL IS ACCREDITED BY THE US DEPARTMENT OF COMMERCE, NATIONAL VOLUNTARY LABORATORY ACCREDITATION PROGRAM FOR SPECIFIC ACOUSTICAL TEST METHODS. THE LABORATORY'S ACCREDITATION OR ANY OF ITS TEST REPORTS IN NO WAY CONSTITUTES OR IMPLIES PRODUCT CERTIFICATION, APPROVAL OR ENDORSEMENT BY NIST OR RAL.

THIS REPORT SHALL NOT BE MODIFIED OR PARTIALLY REPRODUCED WITHOUT THE WRITTEN APPROVAL OF RAL.

THE RESULTS REPORTED APPLY ONLY TO THE SPECIFIC SAMPLE SUBMITTED FOR MEASUREMENT; RAL ASSUMES NO RESPONSIBILITY FOR THE PERFORMANCE OF ANY OTHER SPECIMEN.